

Wood species: PANGA PANGA

Botanic family	Leguminosae Papilionatae
Botanic type	Milletia
Botanic species	Stuhlmannii
Trade names	Panga Panga
Local names	Anong, Jambirè, Kiboto
Growing areas:	Tropical Africa, particularly Mozambique
Colour:	Yellowish or geyish sapwood , clearly different from reddish brown hardwood , which is very dark at times.
Texture	Gross to medium texture and mainly straight fibre.
Dryness	Drying needs to be carried on slowly to avoid splits and deformations.
Durability	Hardwood is very resistant to biological alterations of every type, while sapwood is easily attacked by insects.

Wood species: PANGA PANGA

	VOLUME	HARDNESS (Jank)	DURABILITY	OXYDATION	STABILITY	NERVOUSNESS
Very high	1000	1000				
High	900	850				
Medium	800	700				
Low	700	550				
Very low	600	400				

Remarks: volume refers to the wood with a 12% moisture content